



Hardness Testing


Equotip 550 Portable Rockwell

Equotip 550 Portable Rockwell



Resolution & depth

The only portable measurement method that has practically no minimal thickness limitation - perfect for thin sheets of metals, any material.



Versatility

Equally reliable, accurate and standardized but faster than stationary Rockwell hardness testers.



User Experience

Material independent method - that can be combined with Leeb and UCI in one measurement device. One device - all applications.



Equotip 550 Platform

Tech Specs

Equotip 550 Platform

| | |
|--|---|
| Display | 7" color capacitive touchscreen |
| Instrument protection | <ul style="list-style-type: none">- IP54, fully rugged with shock absorbing casing,- Scratch-resistant Gorilla® Glass screen protection,- Circuit and connector protection against dust, debris, chemicals and voltage spikes- Foldable additional screen cover for additional protection during storage and transportation |
| Memory | Internal 8 GB flash memory (>1'000'000 measurements) |
| Combination with another testing method | Leeb, UCI |
| Connectivity | Ethernet & USB-B (PC connection), USB-A (PRT), Probe-specific slots |
| Battery | 3.6V, Li-Ion, 14'000 mAh |
| Battery lifetime | > 10h (in standard operating mode) |
| Charging time | < 9h, <5.5 h (External quick charger) |
| Power input | 12V +/- 25% / 1.5A |
| Dimensions | 250 x 162 x 62 mm / 9.87 x 6.37 x 6.44 in |
| Weight | 1'525 g / 3.35 lbs. (incl. battery) |
| Humidity operation | < 95% RH, non-condensing |
| Operating temperature | (-) 10°C + 50°C / 14°F – 122°F |
| Certification | CE, KC, FCC |
| Equotip 550 Software Features | <ul style="list-style-type: none">- Advanced algorithm option for faster measurements- Fully customizable reporting- Customizable views- Verification wizard- Measurement wizard- Mapping wizard- Integration in automated testing environments (incl. remote control)- Custom conversion curves (1-point, 2-point, polynomial)- Built-in pdf creator |
| Conversion curves applicable for materials | <ul style="list-style-type: none">- Steel and cast steel |
| Languages | English, German, French, Italian, Spanish, Portuguese, Turkish, Chinese, Korean, Russian, Japanese, Polish, Czech |
| Regional settings | Metric and imperial units, multi-language and time-zone |
| Audio support | Full digital audio |

Desktop Software (Windows)

| | |
|------------------|---|
| PC Software | Equotip Link for data download, management and export (CSV, PNG), Conversion curve management, and for upgrades of constantly expanding Equotip and Equotip Link Software |
| Language support | English, Chinese, Czech, German, Spanish, French, Italian, Korean, Japanese, Polish, Portuguese, Russian, Turkish |



Instrument

Tech Specs

| | |
|------------------------------|---|
| Native Scale | mm, HRC |
| Conversion scales | HLD, HV, HB, HRA, HRB, HRC, HR15N, MPA (σ_1 , σ_2 , σ_3) |
| Measurement range | 10-100 mm, 19-70 HRC, 35-100 HV |
| Indenter | ASTM E3246 and DIN50157 compliant, 100° diamond |
| Impact energy / Test force | 50 N (10N + 40 N) |
| Accredited calibration | ISO/IEC 17025 |
| Standard compliance | ASTM A3246 DIN 50157 |
| Guidelines | ASTM A370 ASME CRTD-91 DGZFP Guideline MC 1 VDI / VDE Guideline 2616 Paper 1 |
| Conversion standards | ASTM E140 ISO 18265 |
| Measurement resolution | 0.1 μm ; 0.1 HRC; 1 HV |
| Measuring accuracy | $\pm 0.8 \mu\text{m}$; $\sim \pm 1.0$ HRC over entire range |
| Measurement deviation (E) | Lower than DIN 50157 and ASTM E3246 |
| Coefficient of variation (R) | Lower than DIN 50157 and ASTM E3246 |
| Weight | 264 g / 9.3 oz |
| Dimensions | $\varnothing 40$ mm, Length 115 mm |

| Standards & Guidelines | Description |
|---|---|
| ASTM A 370 | |
| ASTM E3246 | This test method covers the determination of the Differential Indentation Depth hardness of metallic materials by the Differential Indentation Depth hardness principle. This standard provides the requirements for Differential Indentation Depth hardness testing... |
| DIN 50157 | |
| DGZfP Guideline MC 1 | |
| Nordtest Technical Reports 424-1, 424-2, 424-3 | |
| VDI / VDE Guideline 2616 Paper 1 | |

SWISS  MADE



Present in +100 countries, we serve inspectors and engineers all over the world with the most comprehensive range of InspectionTech solutions, combining intuitive software and Swiss-manufactured sensors.
www.screeningeagle.com

[Request a quote](#)



Machine translated & automatically generated (English version prevails): 13.03.2024
 Copyright © 2023 Screening Eagle Technologies AG or its affiliates. All rights reserved.

